TECHNICAL DATASHEET

Product Name:	**70%PES 30%VIS - 50 GSM - PLAIN**

Fiber Composition:	70%PES - 30%VIS

Technical Characteristics	**Method**	**Units**	**Values**		
			Target	**Minimum**	**Maximum**
Weight	WSP 130.1 (ERT 40.3-90)	g/m²	50	47,5	52,5
Thickness	WSP 120.6 (ERT 30.5-99)	mm	0,60	0,54	0,66
Tensile Strength - Dry (MD)	WSP 110.4 (ERT 20.2-89)	N / 5 cm	75	60	
Tensile Strength - Dry (CD)	WSP 110.4 (ERT 20.2-89)	N / 5 cm	20	16	
Elongation - Dry (MD)	WSP 110.4 (ERT 20.2-89)	%	40		48
Elongation - Dry (CD)	WSP 110.4 (ERT 20.2-89)	%	140		168
Tensile Strength - Wet (MD)	WSP 110.4 (ERT 20.2-89)	N / 5 cm	70	56	
Tensile Strength - Wet (CD)	WSP 110.4 (ERT 20.2-89)	N / 5 cm	19	15	
Elongation - Wet (MD)	WSP 110.4 (ERT 20.2-89)	%	50		60
Elongation - Wet (CD)	WSP 110.4 (ERT 20.2-89)	%	130		156
Liquid Absortion Capacity	WSP 010.1 (ERT 10.3-99)	gr/gr	10,5	10	20

Originated by:
Mara Comerlati
Purchasing Department

Approved by:
Fabrizio Gerosa
Quality Department

Issue date:
18.06.2021

This document contains data obtained from the manufacturer's technical datasheet